

CIENCIA



Reactante (R), estructura de transición (TS) y producto (P) de la reacción retro-ene de trialil amina.

Simulación por autómatas celulares de las conformaciones espaciales de polielectrolitos*

Carlos Echeverría^{1,2**}, Wilmer Olivares-Rivas² and Kay Tucci³

¹Lab. de Física Aplicada y Computacional, Depto. de Matemática y Física,
Universidad Nacional Experimental del Táchira, Táchira, Venezuela.

²Grupo de Químico-física de Fluidos y Fenómenos Interfaciales, Depto. de Química,
Fac. de Ciencias, Universidad de Los Andes, Mérida, Venezuela. ³SUMA-CeSiMo,
Fac. de Ciencias, Universidad de Los Andes, Mérida, Venezuela.

Recibido: 30-11-05 Aceptado: 10-04-06

Resumen

Hemos llevado a cabo simulaciones del tipo Autómata Celular para un modelo de un polielectrolito en dilución infinita, para reproducir de manera cualitativa sus propiedades conformativas. Nuestros resultados predicen las llamadas estructuras de *collar de perlas*, las cuales se comparan bien con simulaciones de Dinámica Molecular más elaboradas y costosas. Cellular automata simulation of the spatial conformations of polyelectrolytes.

Palabras clave: Automas celulares; polielectrolito; electroneutralidad local.

Cellular automata simulation of the spatial conformations of polyelectrolytes

Abstract

We carried out a Cellular Automata simulation of a model polyelectrolyte solution at infinite dilution, in order to reproduce qualitatively its conformational properties. Our results predict the so called *pearl necklace* structures, which compare favorably with the more elaborated and costly Molecular Dynamics simulations.

Key words: Cellular automata; polyelectrolyte; local electroneutrality.

I. Introduction

Polyelectrolyte (PE) solutions are systems widely studied since they show properties that are of fundamental interest for applications in health science, food industry, water treatment, surface coatings, oil industry, among other fields. In fact, one of the problems found in genetic engineering in the appearance of conforma-

tional changes of the ADN molecule, which is a charged polyelectrolyte (1).

Here we study an infinite dilution polyelectrolyte solution, so that, the interaction among polyelectrolyte macromolecules are negligible. We model the polyelectrolyte as having dissociable functional groups that give rise to charged sites and counter-ions in aqueous solution. The

* Trabajo presentado en el V Congreso de la Sociedad Venezolana de Física, La Universidad del Zulia.
Nucleo Punto Fijo - Edo. Falcón, Venezuela, Noviembre 2005.

** Autor para la correspondencia. E-mail: cechove@ula.ve

long range interactions arising from these multiple charges are responsible for their macroscopic complex properties, which can not be explained by regular polymer theories. The spatial structures of these materials in solution have been studied extensively, particularly with a scaling theory (2, 3) that are not appropriate for highly charged PE. The first simulations carried out for a single chain predicted the formation of groups of monomers, as the fraction of charged monomers increased. Such structures are known as pearl necklaces. The size of such pearls and the distance between them is determined by the balance between the electrostatic repulsion and steric effects.

These pearl necklace structures have also been found in Molecular Dynamics (MD) simulations (4-10). In this paper we are interested in the application of the much simpler Cellular Automata simulation to characterize the main features of a polyelectrolyte that could be responsible for such conformations. The complete simulation of this complex system requires the description of a model in terms of potential or forces. In the MD simulations of Limbach and Holm (4), the monomers are connected along the chain by the finite extendible nonlinear elastic (FENE) bond represented by the potential energy.

$$U_E(r) = -\frac{1}{2} K_E R_0^2 \ln\left(1 - \frac{r^2}{R_0^2}\right) \quad [1]$$

where r is the distance between two bonded monomers, K_E is the elastic bond constant, σ is the monomer diameter, k_B is Boltzmann's constant, T is the absolute temperature and the parameter R_0 represents the maximum extension of the bond between two neighbor monomers. Two charged sites i and j , with charges eq_i and eq_j , a distance r_{ij} apart, interact with the electrostatic Coulomb potential.

$$U_C(r_{ij}) = k_B T \frac{\lambda_B q_i q_j}{r_{ij}} \quad [2]$$

This potential is weighed by the Bjerrum length $\lambda_B = e^2 / [4\pi \epsilon_0 \epsilon_s k_B T]$, where ϵ_s and

ϵ_0 are the solvent permitivity and the vacuum permitivity respectively, e is the electric charge unit. The parameter λ_B is a measure of the strength of the electrostatic force as compared to the kinetic energy. The length ratio σ / λ_B is a measure of the reduced temperature $T / [e^2 / (4\pi \epsilon_0 \epsilon_s k_B \sigma)]$. The short range and van derWaals interaction between any two particles or monomers is represented in the MD simulation by a typical truncated Lennard-Jones potential.

$$U_{LJ}(r_{ij}) = \begin{cases} 4 \epsilon \left[\left(\frac{\sigma}{r_{ij}} \right)^{12} - \left(\frac{\sigma}{r_{ij}} \right)^6 \right] + \epsilon_{cut} & r_{ij} < R_c \\ 0 & r_{ij} > R_c \end{cases} \quad [3]$$

where ϵ is the potential energy well depth and ϵ_{cut} is the cut off energy. This potential prevents the superposition of the bonding monomers. Counter-ions interact via a purely repulsive LJ interaction with $R_c = 2^{1/6} \sigma$.

II. Cellular automata model

Even though in the Cellular Automata simulation we do not use any form of potential energies or forces in an explicit manner, the *rules* for the movement of the different particles must be inspired on a model defined in terms of such potentials. We therefore establish our rules based on the essence of the previous three potentials.

A. Polyelectrolyte chain construction rules

The polymer is constructed by placing the monomers in a three dimensional cubic network of side L and volume L^3 . Each cell then has 26 neighbors and represents a monomer with a monovalent charge +1, -1, or, for a neutral monomer, 0, as depicted in Figure 1 in two dimensions. Out of a total of N monomers in the chain, it is assumed that a given fraction f is charged. The polymer is then constructed by randomly binding consecutive sites in the network. Each monomer could be charged or uncharged, with a distribution chosen randomly. A key step on the construction of the polyion is the spatial location




Figure 1. Celular Automata Model. The dark bonded circles represent the charged monomers, the gray circles are the neutral monomers and the open circles are the counter-ions. The shaded area corresponds to the range volume $\lambda_B = 3\sigma$.

of the dissociated counter-ions. We place the counter-ions also randomly in free cells in the volume around the charged monomer within a distance λ_B , that is, in a volume $(2\lambda_B)^3$ centered on the charged site. The use of the Bjerrum parameter, which is related to the quality of the solvent, ensures the conservation of the total electroneutrality but gives a spatial distribution of counter-ions around the charged sites.

So, each monomer i of the system is represented in a $N \times 4$ matrix where each element $M(mx, my, mz, q_i)$ indicates the i^{th} polymer with charge q_i , that could be -1, +1 or 0, at the positions x, y, z given by the cell label $[mx, my, mz]$. The counter-ions with opposite charge are represented by a similar $fN \times 4$ matrix M_C .

For simplicity we chose monomers with dissociable groups that give a site with a positive charge. We then set the following displacement rules for the different particles:

B. Displacement Rules

Neutral Monomer Particle

1. Locate the unoccupied nearest neighbor sites. The new position where a move could be acceptable are those where it does not superimposed with any other particle in the system and where no bond is broken.

2. Count the amount of monomer particles around the current position and around every unoccupied neighbor, within a cube of volume $(2L)^3$ centered on it.

3. Move the test neutral monomer to the position that has the higher amount of monomers around it, including the current one if it were the case.

Positively Charged Monomer Particle

1. As before, locate the unoccupied acceptable nearest neighbor sites.

2. Count the amount of charge around the current position and around every unoccupied neighbor, within a cube of volume $(2\lambda_B)^3$ centred on it.

3. Move the test positive charged monomer to the position that has the lowest positive charge around it, including the current one if it were the case.

Negatively charged counter-ion

1. Move randomly to an unoccupied site within a cube of volume $(2\lambda_B)^3$ centered on the accepted new position of the corresponding positive monomer in the polymeric chain.

III. Results and Discussion

We denote the position of monomer i with r_i and the distance between two particles i and j with r_{ij} . The center of mass for the chain is then

$$R_s = \frac{1}{N} \sum_{i=1}^N r_i$$

and the center of mass coordinates are $x_i = r_i - R_s$.

A parameter that is useful in the study of the spatial conformations of a polymer is the radius of gyration R_g ,

defined as

$$R_g^2 = \frac{1}{N} \sum_{i=1}^N x_i^2 \quad [4]$$

According with our construction and movement rules, we can vary the length of the chain L , or the number of monomers N , satisfying $L = N\sigma$ and the number of charged monomers, $N_c = fN$. We also take as an independent variable the parameter λ_B which determines the number of cells, of size σ , where the range of the electrostatic attraction between a charged monomer and contra-ion extends. The charge distribution of the sequence of charged and uncharged monomers is determined randomly depending on the initial random seed.

In Figure 2 we show some of the equilibrium conformations obtained for a polyelectrolyte with $N = 100$ monomers, with $\lambda_B = 3\sigma$, for several charge fractions. The line represents the polyelectrolyte, the filled black bonded circles represent the charged monomers. The counter-

ions in solution are represented by open nonbonded circles. For clarity, the neutral monomers are not shown. For a low charge fraction of $f = 0.1$, the polyion presents an elongated string appearance. As the charge fraction is increased the polyion contracts and some groups of monomers tend to form clusters, so that, already for $f = 0.5$, it shows the locally collapsed structures known as pearl necklace. These results are very similar to those obtained by the Molecular Dynamics simulations of Limbach and Holm (2, 4). It is important to notice that for a given total charge, determined by the fraction f , different distributions of the charged monomers give different conformations. To study this behavior, we have carried out simulations with several initial seeds for $N=100$ monomers, with a fixed fraction $f = 0.5$ and a range parameter of $\lambda_B/\sigma = 3$. In Figure 3, we show the temporal evolution of the radius of gyration R_g . In all cases the conformations change from the initial given R_g value to a plateau value that correspond to the equilibrium structures. Figure 3 clearly show that the plateau R_g values, and hence, the final conformations depend on the charge distribution. In Figure 4 we show snapshots of final structures corresponding with the different seeds of Figure 3.




Figure 2. Final polyelectrolyte configuration for different charge fractions f: A) 0.1 B) 0.3 C) 0.5 D) 0.7. The pearl necklace conformations appear as the charge fraction increases.




Figure 3. Evolution of the Radius of Gyration R_g as a function of time steps t , for $N=100$, $\lambda_B / \sigma = 3$ and $f= 0.5$. Each curve corresponds to different random charged sites distributions, obtained with different seeds.




Figure 4. Equilibrium Polyelectrolyte structures in the plateau R_g region for the charge of distributions of Figure 3. A) seed1, B) seed2, C) seed3 and D) seed4.

As we can see from Figure 4, the formation of the pearl necklace structures is independent of the charge sites distribution, for a given f and λ_B . These clusters seem to be stabilized by the counter-ions as a consequence of the electroneutrality condition that we force to be satisfied.

This is so because in our model the degree of freedom of the mobile counter-ions is much

higher than that of the monomers tied to the chain. The strong repulsions that originate by the formation of clusters of neutral and positively charged monomers is compensated by the counterion cloud that forms around it.

In order to study the reproducibility of the configurations found, we carried out a large




Figure 5. Histograms for R_g for $N = 150$, $f = 0.5$ and two values of λ_B / σ , A) 3 and B) 9.




Figure 6. Polyelectrolyte conformations for several values of the reduced Bjerrum parameter λ_B / σ A) 3,B) 6,C) 9 and D) 12. Here $f = 0.9$ and $N = 100$ and we used the same initial charge distribu-

number of simulation runs, for fixed values of $N = 150$, $f = 0.5$, $\lambda_B / \sigma = 3$ and 9 and for the same initial charge distribution. In Figure 5 we show the histograms for the frequency with which a given value of R_g appears. We can see that the distribution of the R_g is very closely a gaussian with a reasonably low dispersion of less than a 10% about the mean value.

In Figure (5B) we can see that similar distribution is obtained when the range parameter λ_B / σ increases to a value of 9. We have further tested the effect of the parameter λ_B by generating structures for different values of it. In Figure 6 we show some equilibrium conformations for λ_B / σ equal to A) 3,B) 6,C) 9 and D) 12. Here we use a large charge fraction $f = 0.5$ and $N = 100$ and we used the same initial charge distributions in

all cases. As we can observe as Bjerrum length increases the final polyelectrolyte structures become more compact. The number of pearls or conglomerates is higher for the lower values of λ_B a result similar to that obtained by MD simulations of Limbach y Holm [4]-[10]

IV. Conclusions

With the simple technique described here, we were able to reproduce the complex structure of model polyelectrolytes that fare very well with those predicted by the more sophisticated Molecular Dynamic and Monte Carlo simulations (2, 4). We even predict situations with single conglomerates and with pearl necklace type conglomerates. We thus show the potentiality of the Celular Automata in the simulation of the trends in the formation of the various types of spatial conformations of polyelectrolytes. We remark on the importance of the charge distribution once the fractional charge is fixed.

V. Acnowledgement

This work was supported in part by the grant 04-005-01 from the Decanato de Investigación of Universidad Nacional Experimental del Táchira, in part by the grant G-9700741 of FONACYT, and in part by the grant C-1279-0402-B from Consejo de Desarrollo Científico Hu-

manastico y Tecnológico of Universidad de Los Andes.

References

1. YASMASAKI Y., TERAMOTO Y., YOSHIKAWA K. *Biophys J* 80: 2823-2832, 2001.
2. DOBRYNIN A.V., COLBY R.H., RUBINSTEIN M. *Macromolecules* 28:1859-1871, 1995.
3. DOBRYNIN A.V., RUBINSTEIN M., OBUKHOK S.P. *Macromolecules* 29: 2974-2979, 1996.
4. LIMBACH H.J., HOLM C. *J Phys Chem B* 107, 8041- 8055, 2003.
5. MICKA U. HOLM C. KREMER K. *Langmuir* 15: 4033-4044, 1999.
6. MICKA U., KREMER K. *Europhys Lett* 49:189-195, 2000.
7. LIMBACH H.J., HOLM C. *J Chem Phys* 114: 9674-9682, 2002.
8. LIMBACH H.J., HOLM C. *Comput Phys Commun* 147: 321-324, 2002.
9. LIMBACH H.J., HOLM C. KREMER K. *J Phys Condens Matter* 15: S205-S211, 2003.
10. LIMBACH H.J., HOLM C. KREMER K. *Europhys Lett* 60: 566-572, 2002.

CIENCIA

An International Refereed Scientific Journal of the Experimental Faculty of Sciences at La Universidad del Zulia devoted to publish original research in Biology, Chemistry, Computer Sciences, Mathematics, and Physics

Maracaibo, Venezuela

JOSÉ FERMÍN, Executive Editor

LEONARDO RODRÍGUEZ, Associate Editor

CARLOS DE LA CRUZ, Honorary Editor

Editorial Board

Miguel de la Guardia, Universidad de Valencia (España)

K.H. Rahm, Wilhelms Universität (Alemania)

Alan Hinchliffe, UMIST (UK)

David J. Schiffrin, The University of Liverpool (UK)

Ralph Sturgeon, National Research Center (Canada)

Eduardo R. Chávez, McGill University (Canada)

Jerome O. Nriagu, The University of Michigan (USA)

Mario Werner, The George Washington University (USA)

Sergio M. Rezende, UFPE (Brasil)

Antonio A. Costa, UFPE (Brasil)

José Luis Paz, La Universidad Simón Bolívar (Venezuela)

Jean L. Salager, Universidad de Los Andes (Venezuela)

Jesús González, Universidad de Los Andes (Venezuela)

Ángel Domingo Rueda, La Universidad del Zulia (Venezuela)

Bernardo Rodríguez Iturbe, Universidad del Zulia (Venezuela)

Héctor Severeyn, Universidad del Zulia (Venezuela)

Rodolfo Salas, Universidad del Zulia (Venezuela)

Aleixis Ferrer, Universidad del Zulia (Venezuela)

Gladys León de Pinto, Universidad del Zulia (Venezuela)

Jesús Andrade, Universidad del Zulia (Venezuela)

Rubén Cadenas, Universidad del Zulia (Venezuela)

Carlos Durante, Universidad del Zulia (Venezuela)

José Eli Rincón, Universidad del Zulia (Venezuela)

Pío Arias, UCV (Venezuela)

Marinela Colina, Universidad del Zulia (Venezuela)

Roberto Bauza, Universidad del Zulia (Venezuela)

Marinés Montiel, Universidad del Zulia (Venezuela)

Nelson Marquez, LUZ-Fundacite-Zulia (Venezuela)

Managing Editors

José Manuel Sánchez, Alexander Moronta

Secretary

Aída E. Franco de Araujo

Assistant

Daipedrina Medina

This Journal is covered in:

Analytical Abstracts (RSC), Aquatic Sciences and Fisheries Abstracts (ASFA)
Bibliography and Index of Geology, Chemical Abstracts, Latindex, Physics Abstracts, Revencyt,
Zoological Record, Zentralblatt für Mathematik / Mathematics Abstracts

Esta revista fue impresa en papel alcalino cumpliendo con los requerimientos mínimos de la Estándar Nacional Americana para el Registro Permanente de Materiales para Publicaciones Científicas, ANSI Z39.48-1984

This publication was printed on acid-free paper that meets the minimum requirements of American National Standard for Information Sciences—Permanence for Paper for Printed Library Materials, ANSI Z39.48-1984

This journal is supported by
the Council for Scientific and Humanistic Development of La Universidad del Zulia (CONDES)

CIENCIA

Revista Científica de la Facultad Experimental de Ciencias de La Universidad del Zulia
Vol. 14 N° 4, October-December 2006

Pg.

BIOLOGÍA/BIOLOGY

Crecimiento de microalgas de agua dulce, en dos medios de cultivo Guillard y un fertilizante comercial Nitrofoska
Growth of microalgae of fresh water, in two culture media Guillard and Nitrofoska a commercial fertilizer
Diagnora Brito, Nadia Milani, Guido Pereira, Mario Gonzalez y Rodolfo Moran (Caracas, Venezuela)

397

Antimicrobial activity of extracts from *Ageratina nerifolia* (Asteraceae)

Actividad antimicrobiana de los extractos de *Ageratina nerifolia* (Asteraceae)

Judith Velasco, Silvio Barreto, Diolimar Buitrago y Rosana Vivas (Mérida, Venezuela)

411

COMPUTACIÓN/COMPUTATION

Efecto de la distancia del medio de transmisión en el rendimiento de redes ethernet

Transmission media length effect on ethernet networks performance

Carlos A. Rincón C., Alfredo J. Acurero, David R. Bracho, Carmen E. Castro de R. y Desirée L. Arias (Maracaibo, Venezuela)

415

FÍSICA/PHYSICS

Modelling tropospheric radio-attenuation parameters for tropical countries. The Venezuela case

Modelando parámetros de radio-attenución troposférica para países tropicales. El caso Venezuela

Ángel G. Muñoz S., Ronald Pacheco, Nestor Cubillán, Carlos Alberto Durante Rincón, Larissa Durán y José Fermín (Maracaibo, Venezuela)

428

Estudio estructural a altas presiones del MnGa₂Se₃

High-Pressure structural study of MnGa₂Se₃

Jesús Marquina, Chrystian Power, Pedro Grima, Manuel Morocoima, Miguel Quintero, Bernard Couzinet, Jean-Claude Chervin, Pascal Munsch y Jesús González (Mérida, Venezuela)

435

Influence of the dynamical parameters and viral mutability in the progression of HIV-1 infection

Influencia de los parámetros dinámicos y la mutabilidad viral en la progresión de la infección por VIH-1

Horacio Ortega (Caracas, Venezuela)

440

Simulación por autómatas celulares de las conformaciones espaciales de polielectrolitos

Cellular automata simulation of the spatial conformations of polyelectrolytes

Carlos Echeverria, Wilmer Olivares-Rivas and Kay Tucci (Mérida, Venezuela)

452

Investigaciones mediante espectroscopía de resonancia paramagnética electrónica en la degradación de la mezcla PS/PP (80/20) 30wt% SBS con 0,1% Recyclostab 811, irradiada con rayos gamma, después de 4 años de almacenamiento en atmósfera de oxígeno

Electronic paramagnetic resonance investigations on degradation of PS/PP (80/20) blend with 30 wt% SBS, and 0.1wt%, recyclostab 811, under gamma irradiation, after 4 years of oxygen storage

Ernesto Davidson, Delfín Moronta, Jacobo Reyes-Romero y Rosalba Sciamanna (Caracas, Venezuela)

459

Método iterativo en sistemas moleculares interactuando con campos eléctricos dependientes del tiempo

Iterative method in molecular systems interacting with time dependents electric fields

José Luis Paz y Inés Urdaneta (Caracas, Venezuela)

465

QUÍMICA/CHEMISTRY

Cálculo de la energía de activación de la reacción retro-ene de eliminación de propileno a partir de triallyl amina

Activation energy calculation of the retro-ene elimination reaction of propylene from triallyl amine

Alba B. Vidal, Rafael Áñez, Rodolfo E. Izquierdo y Leonardo J. Rodríguez (Maracaibo, Venezuela)

481

Extracts from *Pera glabrata* (Schott) and *Pera distichophylla* with anti parasite and antiviral activity

Extractos de *Pera glabrata* (Schott) y *Pera distichophylla* con actividad antiparasitaria y antiviral

Morella Rodríguez-Ortega, Diana Luna, Yeilis Canónico, Zaida Carvajal, Jeannette Méndez y Luis Briceño (Caracas, Venezuela)

492

Estudios de formación de complejos de cromo (III) con los ácidos picolinico y dipicolínico en solución acuosa

Chromium (III) complexes formation studies with picolinic and dipicolinic acids in aqueous solution

Mary Luz Lugo, Freya Da Costa y Vito Lubes (Caracas, Venezuela)

498

Remoción de materia orgánica y nutrientes utilizando dos especies de plantas emergentes

Removal of organic matter and nutrients by employing of two emergent plant species

Marisel Núñez, Kiamelis Dubuc, Juan Pablo Paz, Luisa Saules, Alberto Trujillo, Carmen Cárdenas y Ever Morales (Maracaibo, Venezuela)

506

Modificación y evaluación de un horno de microondas doméstico para la digestión en envases abiertos de muestras de orina y sangre

Modification and evaluation of a domestic microwave oven for open-vessel digestion of urine and blood samples

Diego Alizo, José R. Domínguez V., Ivelin Morales-Fuentes y José Alvarado D. (Caracas, Venezuela)

516

Indice de Autores

525

Subject Index

528

Indice Acumulado

531

CIENCIA

Aim and Scope

CIENCIA publishes original papers, preliminary communications, technical notes, and reviews dealing with modern scientific aspects of Biology, Computer Sciences, Mathematics, Physics and Chemistry. Relevant papers in Environmental Chemistry and Food Chemistry are also invited to be submitted. Manuscripts should be addressed to: Dr. José Fermín (Executive Editor) or Dr. Leonardo Rodríguez (Associate Editor). Editorial Office of CIENCIA, Facultad Experimental de Ciencias, La Universidad del Zulia, Maracaibo 4001-A, Venezuela. Telephone: +58 261 7597719, 7598098. Tel-Fax: +58 261 7598099. Apartado postal 15625-OP, Galeria Mall, Maracaibo, Venezuela. E-mail: jfermin@luz.edu.ve; leon@luz.edu.ve; revista_ciencia@yahoo.com; publicaciones.fecs@luz.edu.ve

Description

Manuscripts submission is understood to imply that the article is original and unpublished and is not being considered for publication elsewhere. CIENCIA accepts papers in English and in Spanish only. There are no pages charge. Manuscripts should conform in layout and style to the papers published in this issue. See the "Instruction for Authors" that appear in every issue of CIENCIA.

Publication

CIENCIA (ISSN 1315-2076/Depósito legal pp 199302ZU47) is a publication of the Faculty of Sciences at La Universidad del Zulia. Appeared in 1993 (Vol. 1) with two issues yearly. Volume 2 appeared in 1994 (two issues). Volume 3 appeared in 1995 (three issues). Vol. 4 appeared in 1996 (four issues). Volume 5 appeared in 1997 (three issues). Vol. 6 appeared in 1998 (three issues). Vol. 7 appeared in 1999 (three issues). Vol. 8 appeared in 2000 (three issues). Vol. 9 appeared in 2001 (Four issues). Vol. 10 appeared in 2002 (Four issues) Vol. 11 appeared in 2003 (Four issues) Vol. 12 appeared in 2004. Vol. 13 appeared in 2005. Vol. 13 appears in 2005. The articles published in this Journal are protected by Copyright.

CIENCIA

Alcance

CIENCIA publica artículos originales, comunicaciones preliminares, notas técnicas, comunicaciones cortas y revisiones relacionadas con todos los aspectos científicos modernos de la Biología, Ciencias de la Computación, Matemáticas, Física y Química. Artículos significativos en el área de Química Ambiental y Química de los Alimentos también pueden ser publicados en CIENCIA. Los manuscritos deben ser dirigidos a: Dr. José Fermín (Executive Editor) or Dr. Leonardo Rodríguez (Associate Editor). Editorial Office of CIENCIA, Facultad Experimental de Ciencias, La Universidad del Zulia, Maracaibo 4001-A, Venezuela. Telephone: +58 261 7597719, 7598098. Tel-Fax: +58 261 7598099. E-mail: jfermin@luz.edu.ve; leon@luz.edu.ve; revista_ciencia@yahoo.com; publicaciones.fecs@luz.edu.ve

Descripción

El envío de un manuscrito a CIENCIA supone que éste es original y no ha sido publicado ni está siendo considerada su publicación en otra revista. CIENCIA acepta manuscritos en español y en inglés. No hay cobro por página. Los manuscritos deben adaptarse al estilo de los artículos publicados en este número. Los autores deben guiararse por las condiciones expuestas en la sección de "Instrucciones para Autores", que aparecen en cada número de CIENCIA.

Publicación

CIENCIA (ISSN 1315-2076/Depósito legal pp 199302ZU47) es una publicación de la Facultad Experimental de Ciencias de La Universidad del Zulia. El Vol. 1 (1993) y el Vol. 2 (1994) aparecieron con dos números al año. El Vol. 3 (1995), el Vol. 4 (1996), el Vol. 5 (1997), el Vol. 6 (1998), el Vol. 7 (1999) y el Vol. 8 (2000), aparecieron con tres números al año. El Vol. 9 (2001), el Vol. 10 (2002), el Vol. 11 (2003), el Vol. 12 (2004) y el Vol. 13 (2005) aparecieron con cuatro números al año. El Vol. 14 aparece en el año 2006. CIENCIA es publicada por La Universidad del Zulia.